

# BEZILLO<sup>®</sup>

SUPERIOR QUALITY PRODUCTS.

## EPOTIX SPECIAL



# BEZILLO EPOTIX SPECIAL

## PRODUCT DESCRIPTION

High adhesion and mechanical strength bi-component Epotix Special with property of High UV and weather resistance.

It is recommended for strong and durable joining or grouting of marbles, granites and natural and artificial stones in general. Due to its extremely low shrinkage and high tixotropicity, the product shows excellent performances in vertical application and holes filling.

## INSTRUCTIONS OF USE

In order to maximize product performances, the following instructions should be followed:







- Before using the glue check that the surface has to be dry, clean and dust free.
- Use a spatula to take the necessary quantity of Part A and an other spatula for take the necessary quantity of Part B.
- Pay attention to not add the Part B inside the can of Part A

- Mix thoroughly the two dosed components with ratio by weight of 2:1 (A:B), using small quantities of product in order to avoid too fast curing.
- For color the glue use Bezillo Colorant Paste, add the colour to the glue, max 3%, before and then add the hardener in paste.
- Keep in original packing. Avoid to use product with temperature below 10°C (50°F). Only for professional use.

## STORAGE AND SAFETY

If stored in original containers in dry and clean environment (minimum Temperature around 15°C), the product can be used up to 1 year from production date. The product should never be exposed to direct sunlight and used below 15°C. The product must be always used in aerated ambient wearing the suitable Personal Protective Equipment. Before use, Material Safety Data Sheets must be carefully looked up.

## ADVANTAGES

-  ... Superior quality knife grade epoxy glue with extra strong bonding
-  ... Very low yellowing
-  ... Excellent adhesion & reactivity in all temperatures
-  ... Low shrinkage
-  ... Gives good gloss and brightness after polishing
-  ... Mixing ratio – 2:1 (a+b)

## DISCLAIMER

This information is true and accurate to the best of our knowledge and belief, but since the circumstances of use and any labour required are out of our control, the end user must verify beforehand that the product is appropriate for his particular application. No responsibility can be accepted, and no warranty can be provided by our Representatives, Agents, or Distributors. The end user should make sure he has read our most recent material and that the products are sold in accordance with our Standard Conditions of Sale.

# BEZILLO EPOTIX SPECIAL

## TECHNICAL DATA SHEET

### PROPERTIES OF SINGLE COMPONENTS

	Resin	Hardener
Appearance	Colorless Tixotropic Paste	Colorless Tixotropic Paste
Density 25°C	1,10-1,20 g/ml	1,00-1,10 g/ml
Smell	Low	Low

### PROPERTIES OF THE SYSTEM

Mixing ratio (weight)	Resin : Hardener	100 : 50
Gel Time	25°C	25 <sup>m</sup> -35 <sup>m</sup>
Workability 20°C	Small Pieces Handling	4h-6h
	Sanding/Grinding	8h-10h



EXPERIENCE THE DIFFERENCE!!

**BETON STONE SOLUTIONS INDIA PVT LTD**

+91 99301 28291 / +91 83286 36546

[info@betonstonesolutions.com](mailto:info@betonstonesolutions.com) | [www.betonstonesolutions.com](http://www.betonstonesolutions.com)

**HEAD OFFICE - INDIA**

B/2, Amrat Niwas, 15th  
Sarojini Road, Ville Parle  
(W), Mumbai - 400056, India.

**REGIONAL OFFICE - INDIA**

Plot No.18, Saibabanagar  
Colony, Tellapur, R.C. Puram,  
Sangareddy, Hyderabad, India.

**ITALY OFFICE**

Via Monte Cengio,  
11/0 36073, Cornedo  
Vicentino (VI) Italy.

**DUBAI OFFICE**

P.O. Box  
239697,  
Dubai UAE.